



Kaleidoscope Triangle Pattern Bar Mold

Create your finished project

When your pattern bar is fully cooled, use a diamond blade wet saw to cut the bar into slices, approximately 1/4" or 6-7 mm thick.

Design your project with your beautiful new glass slices and fire to full fuse. You can fill any small gaps with frit if necessary.

Plate Firing Schedule

Rate per/hr	Temp	Hold
500 °	450	25 min
500 °	1235	30 min
500 °	1460	30 min
AFAP	950	3 hrs
50 °	800	0
Cool to room temperature		

